

3M™ Sun Control Window Film


# Ceramic Architectural CA35



## Heat rejection with high clarity and enhanced views

### Benefits

- ▶ Helps reduce glare which provides excellent aesthetics
- ▶ Low interior and exterior reflectivity enhances views while maintaining exterior appearance
- ▶ Stay cooler by reducing excessive heat in warmer months
- ▶ Non-metalized film with natural tone for amazing clarity
- ▶ Helps extend the life of furnishings by significantly reducing harmful UV rays, the largest cause of fading
- ▶ Comprehensive warranty from 3M



© 3M 2024. All rights reserved. 3M is a trademark of 3M. Used under license in Canada. All other trademarks are property of their respective owners. Please recycle. 75-5100-2952-5

3M Commercial Branding and Transportation Division  
3M Center, Building 223-3N-30  
St. Paul, MN 55144-1000  
3M.com/windowfilm



Warranty and Limited Remedy: 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER EXPRESS OR IMPLIED WARRANTIES OR CONDITIONS, INCLUDING ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If the 3M product does not conform to this warranty, the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price. Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted.

**LEED Certification**  
Window films may be used toward the following LEED credits:

◀ EA-1	◀ EQ-7.1	◀ MR 5.1-5.2	◀ EQ-8.1-8.2
◀ SS-8	◀ EQ-7.1	◀ EQ-7.2	◀ ID

## Product Performance and Technical Data

Glass Type (All 1/4")	Film Type (Interior)	Visible Light Reflected (Exterior)	Visible Light Transmitted	Total Solar Energy Rejected	Solar Heat Gain Coefficient (G Value)	U Value wv/hft <sup>2</sup> F	U Value w/m <sup>2</sup> K	Solar Heat Reduction	UV Light Reduction	Glare Reduction	Visible Light to Solar Heat Gain Ratio
Clear	CA35	6%	6%	37%	0.45	1.02	5.8	45%	99.8%	58%	0.8
Tinted	CA35	5%	6%	22%	0.40	1.02	5.8	37%	99.8%	58%	0.6
Double Clear	CA35	7%	13%	33%	0.56	0.47	2.7	20%	99.7%	58%	0.6
Double Tinted	CA35	6%	8%	20%	0.42	0.47	2.7	18%	99.9%	58%	0.5